

Paper Weight Conversion Chart

The darker boxes below represent the "most common paper weights" for that category

| Bond Ledger | Offset Text | Cover | Tag | Index | Points | Mil | Millimeters | Gauge | *Caliper (inch) | Metric (grams/sq meter) |
|-------------|-------------|-------|-----|-------|--------|------|-------------|-------|-----------------|-------------------------|
| 16 | 40 | 22 | 37 | 33 | 3.2 | 3.2 | 0.081 | | 0.0032 | 60.2 gsm |
| 18 | 45 | 24 | 41 | 37 | 3.6 | 3.6 | 0.092 | | 0.0036 | 67.72 gsm |
| 20 | 50 | 28 | 46 | 42 | 3.8 | 3.8 | 0.097 | | 0.0038 | 75.2 gsm |
| 24 | 60 | 33 | 56 | 50 | 4.8 | 4.8 | 0.12 | | 0.0048 | 90.3 gsm |
| | | | | | | 5 | | 5 | 0.005 | |
| 28 | 70 | 39 | 64 | 58 | 5.8 | 5.8 | 0.147 | | 0.0058 | 105.35 gsm |
| 29 | 73 | 40 | 62 | 60 | 6 | 6 | 0.152 | 6 | 0.006 | 109.11 gsm |
| 31 | 81 | 45 | 73 | 66 | 6.1 | 6.1 | 0.155 | | 0.0061 | 116.63 gsm |
| 32 | | | 74 | 67 | | | | | | 120 gsm |
| 35 | 90 | 48 | 80 | 74 | 6.2 | 6.2 | 0.157 | | 0.0062 | 131.68 gsm |
| 36 | 90 | 50 | 82 | 75 | 6.8 | 6.8 | 0.173 | | 0.0068 | 135.45 gsm |
| 39 | 100 | 54 | 90 | 81 | 7.2 | 7.2 | 0.183 | | 0.0072 | 146.73 gsm |
| | | | | | | 7 | | 7 | 0.007 | |
| 40 | 100 | 56 | 93 | 83 | 7.3 | 7.3 | 0.185 | | 0.0073 | 150.5 gsm |
| 43 | 110 | 60 | 100 | 90 | 7.4 | 7.4 | 0.188 | | 0.0074 | 161.78 gsm |
| 44 | 110 | 61 | 102 | 92 | 7.6 | 7.6 | 0.193 | | 0.0076 | 165.55 gsm |
| 47 | 120 | 65 | 108 | 97 | 8 | 8 | 0.198 | 8 | 0.0078 | 176.83 gsm |
| 53 | 135 | 74 | 122 | 110 | 9 | 9 | 0.216 | 9 | 0.0085 | 199.41 gsm |
| 54 | 137 | 75 | 125 | 113 | 9 | 9 | 0.229 | | 0.009 | 203.17 gsm |
| 58 | 146 | 80 | 134 | 120 | 9.5 | 9.5 | 0.234 | | 0.0092 | 218.22 gsm |
| 65 | 165 | 90 | 150 | 135 | 10 | 10 | 0.241 | 10 | 0.0095 | 244.56 gsm |
| 67 | 170 | 93 | 156 | 140 | 10.5 | 10.5 | 0.25 | | 0.01 | 252.08 gsm |
| 72 | 183 | 100 | 166 | 150 | 11 | 11 | 0.289 | 11 | 0.011 | 270.9 gsm |
| | | | | | | 12 | | 12 | | |
| 76 | 192 | 105 | 175 | 158 | 13 | 13 | 0.33 | 13 | 0.013 | 285.95 gsm |
| 82 | 208 | 114 | 189 | 170 | 14 | 14 | 0.356 | 14 | 0.014 | 308.52 gsm |
| 87 | 220 | 120 | 200 | 180 | 15 | 15 | 0.38 | 15 | 0.015 | 312 gsm |
| | | | | | | 26 | | 16 | | |
| 105 | 267 | 146 | 244 | 220 | 18 | 18 | 0.445 | | 0.0175 | 385.06 gsm |
| | | | | | | 20 | | 20 | | |

*Normal paper manufacturing tolerance within a paper production run is + or - 5% to 7% caliper